



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) **EP 0 980 890 A1**

(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:
23.02.2000 Bulletin 2000/08

(51) Int. Cl.⁷: C08J 9/14, C09K 5/04

(21) Application number: 99114824.8

(22) Date of filing: 29.07.1999

(84) Designated Contracting States:
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE
Designated Extension States:
AL LT LV MK RO SI

(30) Priority: 19.08.1998 IT MI981905

(71) Applicant: Ausimont S.p.A.
20121 Milano (IT)

(72) Inventors:
• Musso, Ezio
Castelletto D'Orba, Alessandria (IT)
• Basile, Giampiero
Alessandria (IT)
• Girolimoni, Sauro
Spinetta Marengo, Alessandria (IT)

(74) Representative:
Sama, Daniele, Dr. et al
Sama Patents,
Via G.B. Morgagni, 2
20129 Milano (IT)

(54) **Fluorinated foaming compositions**

(57) Use as foaming agents having a low environmental impact of azeotropic or near azeotropic compositions using difluoromethoxy-bis(difluoromethyl ether) and/or 1-difluoromethoxy-1,1,2,2-tetrafluoroethyl difluoromethyl ether.

EP 0 980 890 A1

Description

[0001] The present invention relates to azeotropic or near azeotropic compositions to be used as trichlorofluoromethane (CFC 11) substitutes in the foaming field.

[0002] More specifically the present invention relates to azeotropic or near azeotropic mixtures characterized by zero ODP (Ozone Depletion Potential), low GWP (Global Warming Potential) and VOC (Volatile Organic Compounds) values.

[0003] The foamed polyurethanes represent a class of materials widely used for applications concerning the furnishing, car and in general transport, building and cooling industry.

[0004] Polyurethanes are polyaddition products between isocyanates and polyols; depending on the precursor features, it is possible to obtain flexible, rigid foams, or foams having intermediate characteristics.

[0005] The former are used in the furnishing and car sector, while rigid polyurethanes are widely used in the thermal insulation field for building and cooling industry.

[0006] All the polyurethane foams require a foaming agent for their preparation in order to obtain cellular structures, density, mechanical and insulation properties suitable for any application type.

[0007] As known, the common foaming agent used for the preparation of foamed polyurethanes has been for a long time CFC 11.

[0008] CFCs and specifically CFC 11 have, however, the drawback to show a high destroying power on the stratospheric ozone layer, therefore, the production and commercialization have been subjected to rules and then banned since January 1, 1995.

[0009] In the foamed polyurethane field, the use versatility of these products, which allows applications in different fields with the use of suitable technologies and raw material formulations, has made impossible the identification of a single product valid for the replacement of CFC 11 in all applications.

[0010] The alternative solutions which now result widely used foresee the use of hydrocarbons (n-pentane, isopentane and cyclopentane) or of HCFC 141b (1,1-dichloro-1-fluoroethane).

[0011] Hydrocarbons, due to their high flammability, have not a generalized use and require large investments to avoid fire and explosion risks in plants using them. Furthermore, these foaming agents constitute an atmospheric pollution source since, if exposed to the sun light in the presence of nitrogen oxides, they undergo oxidative degradation phenomena, with formation of the so called ozone-rich "oxidizing smog". Due to this negative characteristic, these products are classified as VOC compounds (Volatile Organic Compound). HCFC 141b, which has been and is one of the most valid substitutes for above applications, has however the drawback to be moderately flammable and especially to be characterized by an ODP value equal to 0.11 (CFC 11 has ODP=1) and therefore it has been subjected to restricted use. There was a need to have available substitutes able to furtherly limit or overcome the above mentioned environmental and safety problems and which allow a simpler and generalized use as foaming agents.

[0012] In a previous patent application in the name of the Applicant foaming compositions using specific hydrofluoropolyethers have been described. However said hydrofluoropolyethers are very expensive for their obtainment process.

[0013] The need was therefore felt to have available foaming compositions based on said hydrofluoropolyethers (HFPE) having an azeotropic or near azeotropic behaviour as to be used as substitute of CFC 11 but with low environmental impact expressed in terms of ODP, GWP and VOC values.

[0014] The Applicant has unexpectedly found that the hydrofluoropolyether-based mixtures (HFPE), object of the present invention, are characterized by chemical-physical properties such to be suitable as substitutes of CFC 11, they have an environmental impact expressed in terms of ODP equal to zero and low GWP and VOC values.

[0015] It is an object of the present invention azeotropic or near azeotropic compositions to be used as foaming agents having a low environmental impact, consisting essentially of:

		composition % by weight	
		general	preferred
I)	difluoromethoxy bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$);	1-95	25-95
	n-pentane	99-5	75-5
II)	difluoromethoxy bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$);	1-99	25-98
	iso-pentane	99-1	75-2

(continued)

		composition % by weight	
		general	preferred
5	III) difluoromethoxy bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$); dimethyl ketone (acetone)	1-60 99-40	20-60 80-40
	IV) difluoromethoxy bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$); 1,1,1,3,3-pentafluorobutane ($\text{CF}_3\text{CH}_2\text{CF}_2\text{CH}_3$, HFC 365 mfc)	1-99 99-1	10-98 90-2
10	V) difluoromethoxy bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$); 1,1,1,4,4,4-hexafluorobutane ($\text{CF}_3\text{CH}_2\text{CH}_2\text{CF}_3$, HFC 356 ffa)	1-40 99-60	10-40 90-60
	VI) difluoromethoxy bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$); methoxymethyl methylether	1-96 99-14	25-96 75-14
15	VII) difluoromethoxy bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$); n-hexane	30-99 70-1	35-98 65-2
	VIII) 1-difluoromethoxy 1,1,2,2-tetrafluoroethyl difluoromethyl ether ($\text{HCF}_2\text{OCF}_2\text{CF}_2\text{OCF}_2\text{H}$); n-pentane	1-93 99-7	25-93 75-7
20	IX) 1-difluoromethoxy 1,1,2,2-tetrafluoroethyl difluoromethyl ether ($\text{HCF}_2\text{OCF}_2\text{CF}_2\text{OCF}_2\text{H}$); dimethyl ketone (acetone)	30-99 70-1	50-98 50-2
25	X) 1-difluoromethoxy 1,1,2,2-tetrafluoroethyl difluoromethyl ether ($\text{HCF}_2\text{OCF}_2\text{CF}_2\text{OCF}_2\text{H}$); n-hexane	15-99 85-1	25-98 75-2
30	XI) 1-difluoromethoxy 1,1,2,2-tetrafluoroethyl difluoromethyl ether ($\text{HCF}_2\text{OCF}_2\text{CF}_2\text{OCF}_2\text{H}$); ethyl alcohol	5-99 95-1	10-98 90-2

[0016] Difluoromethoxy-bis(difluoromethyl ether) is indicated as HFPE1; 1-difluoromethoxy-1,1,2,2-tetrafluoroethyl difluoromethyl ether is indicated as HFPE2. More specifically the azeotropic compositions, in correspondence of which an absolute minimum or maximum in the boiling temperature at the pressure of 1.013 bar with respect to the pure products is noticed, are defined as follows:

		Compositions are defined within +/- 2 % by weight
45	A) difluoromethoxy-bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$); n-pentane	62% by wt. 38% by wt.
50	B) difluoromethoxy-bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$); iso-pentane	63% by wt. 36% by wt.
	C) difluoromethoxy-bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$); dimethyl ketone (acetone)	42% by wt. 58% by wt.
55	D) difluoromethoxy-bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$); 1,1,1,1,3,3-pentafluorobutane ($\text{CF}_3\text{CH}_2\text{CF}_2\text{CH}_3$, HFC 365 mfc)	60% by wt. 40% by wt.

(continued)

		Compositions are defined within +/- 2 % by weight
5	E) difluoromethoxy-bis(difluoromethyl ether) (HCF ₂ OCF ₂ OCF ₂ H); 1,1,1,4,4,4-hexafluorobutane (CF ₃ CH ₂ CH ₂ CF ₃ , HFC 356 ffa)	20% by wt. 80% by wt.
10	F) difluoromethoxy-bis(difluoromethyl ether) (HCF ₂ OCF ₂ OCF ₂ H); methoxymethyl methyl ether	59% by wt. 41% by wt.
	G) difluoromethoxy-bis(difluoromethyl ether) (HCF ₂ OCF ₂ OCF ₂ H); n-hexane	75% by wt. 25% by wt.
15	H) 1-difluoromethoxy-1,1,2,2-tetrafluoroethyl difluoromethyl ether (HCF ₂ OCF ₂ CF ₂ OCF ₂ H); n-pentane	61% by wt. 39% by wt.
20	I) 1-difluoromethoxy-1,1,2,2-tetrafluoroethyl difluoromethyl ether (HCF ₂ OCF ₂ CF ₂ OCF ₂ H); dimethyl ketone (acetone)	79% by wt. 21% by wt.
25	L) 1-difluoromethoxy-1,1,2,2-tetrafluoroethyl difluoromethyl ether (HCF ₂ OCF ₂ CF ₂ OCF ₂ H); n-hexane	74% by wt. 26% by wt.
30	M) 1-difluoromethoxy-1,1,2,2-tetrafluoroethyl difluoromethyl ether (HCF ₂ OCF ₂ CF ₂ OCF ₂ H); ethyl alcohol	95% by wt. 5% by wt.

[0017] The mixtures having an azeotropic or near azeotropic behaviour are of great importance in order to avoid fractionation or considerable variations of their composition during handling, dosage and storage operations wherein accidental losses can take place due to liquid evaporation and consequently variations of the composition of the fluid.

[0018] The composition variations which take place in all the cases when non azeotropic mixtures are used, involve deviations of the foaming agent performances and the need to make suitable refillings in order to restore the original composition and therefore the mixture chemical-physical characteristics.

[0019] Furthermore, when the non azeotropic or non near-azeotropic compositions contain more volatile flammable components, the vapour phase becomes rich in such component until reaching the flammability limit, with evident risks for the use safety. Likewise, when the flammable component is less volatile, it concentrates in the liquid phase giving rise to a flammable liquid.

[0020] Mixtures having azeotropic or near azeotropic behaviour avoid the above disadvantage even when a flammable compound is present.

[0021] An azeotrope is a particular composition which has singular chemical-physical, unexpected and unforeseeable properties of which the most important ones are reported hereinafter.

[0022] An azeotrope is a mixture of two or more fluids which has the same composition in the vapour phase and in the liquid one when it is in equilibrium under determined conditions.

[0023] The azeotropic composition is defined by particular temperature and pressure values; in these conditions the mixtures undergo phase changes at constant composition and temperature as pure compounds.

[0024] A near azeotrope is a mixture of two or more fluids which has a vapour composition substantially equal to that of the liquid and undergoes phase changes without substantially modifying the composition and temperature. A composition is near azeotropic when, after evaporation at a constant temperature of 50% of the liquid initial mass, the per cent variation of the vapour pressure between the initial and final composition results lower than 10%; in the case of an azeotrope, no variation of the vapour pressure between the initial composition and the one obtained after the 50% liquid evaporation is noticed.

[0025] Azeotropic or near azeotropic mixtures belong to the cases showing meaningful, both positive and negative, deviations from the Raoult law. As known to the skilled in the art such law is valid for ideal systems.

[0026] When such deviations are sufficiently marked, the mixture vapour pressure in the azeotropic point must therefore be characterized by values either lower or higher than those of the pure compounds.

[0027] It is evident that, if the mixture vapour pressure curve shows a maximum, this corresponds to a minimum of boiling temperature; viceversa to a vapour pressure minimum value, a maximum of boiling temperature corresponds.

[0028] The azeotropic mixture has only one composition for each temperature and pressure value.

[0029] However, by changing temperature and pressure, more azeotropic compositions starting from the same components can be obtained.

[0030] For example, the combination of all the compositions of the same components which have a minimum or a maximum in the boiling temperature at different pressure levels form an azeotropic composition field.

[0031] Hydrofluoropolyethers used in the compositions of the present invention: HFPE1 and HFPE2, are obtained by decarboxylation processes of the alkaline salts obtained by hydrolysis and salification of the corresponding acylfluorides, using processes known in the art. For example, decarboxylation is carried out in the presence of hydrogen-donor compounds, for example water, at temperatures of 140°-170°C and under a pressure of at least 4 atm. See for example EP 695,775 and the examples reported therein; this patent is herein incorporated by reference.

[0032] The characteristics of the two hydrofluoropolyethers used in the compositions of the present invention are reported in Table 1 in comparison with CFC 11 and HCFC 141b as regards ODP and GWP.

[0033] It has been found that the near azeotropic compositions of points II, III, IV, V, VI, remain near azeotropic also when a portion of difluoromethoxy-bis(difluoromethyl ether) is substituted with 1-difluoromethoxy-1,1,2,2-tetrafluoroethyl-difluoromethyl ether, up to 40% by weight. They are used as foaming agents.

[0034] The same for compositions of points IX and X when a portion of 1-difluoromethoxy-1,1,2,2-tetrafluoroethyl difluoromethyl ether is substituted by difluoromethoxy-bis(difluoromethyl ether), up to 40% by weight. They are used as foaming agents.

[0035] The same for compositions of points I and VII wherein a portion of difluoromethoxy-bis(difluoromethyl ether) is replaced by 1-difluoromethoxy-1,1,2,2-tetrafluoroethyl difluoromethyl ether up to 50% by weight. They are used as foaming agents.

[0036] Likewise the compositions of points VIII and X, wherein a portion of 1-difluoromethoxy-1,1,2,2-tetrafluoroethyl difluoromethyl ether is replaced by difluoromethoxy-bis(difluoromethyl ether) up to 50% by weight.

[0037] Another object of the present invention are ternary near azeotropic compositions essentially consisting of:

		% by weight
XII)	difluoromethoxy-bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$);	1-64
	1,1,1,3,3-pentafluorobutane ($\text{CF}_3\text{CH}_2\text{CF}_2\text{CH}_3$, HFC 365 mfc)	98-1
	hydrocarbon	1-35
XIII)	difluoromethoxy-bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$);	1-22
	1,1,1,4,4,4-hexafluorobutane ($\text{CF}_3\text{CH}_2\text{CH}_2\text{CF}_3$, HFC 356 ffa)	98-43
	hydrocarbon	1-35

used as foaming agents.

[0038] Among hydrocarbons, n-pentane and iso-pentane are preferred preferably in the range 1-20% by weight.

[0039] A further object of the present invention are azeotropic or near azeotropic compositions to be used as foaming agents, as described at points from I) to XIII) and from A) to M), wherein a portion of HFPE1 and/or HFPE2 is replaced by hydrofluoropoly-ethers having the same structure of HFPE1 or HFPE2 but boiling point in the range of 5°-80°C. Therefore, it is possible to refer to fluids consisting essentially of HFPE1 and/or HFPE2.

[0040] The compositions mentioned at points I, II, IV, V, VI, VII, VIII, X, A, B, D, E, F, G, H and L are preferred as foaming agents for foamed polyurethanes, and represent a good substitute for CFC 11 for their good balance of foaming properties.

[0041] The polyurethane foams produced with the azeotropic or near azeotropic compositions of the present invention are obtained by reaction between polyols and isocyanates in the presence of catalysts and other additives usually employed for preparing polyurethane foams, by using known methods. Depending on the desired foams to be prepared, polyols and isocyanates will be used such as to obtain in combination with the present invention compositions the chemical-physical and mechanical characteristics required for each specific application.

[0042] Another advantage of the present invention, in the polyurethane foam preparation field, is that to be able to modulate the affinity of the mentioned mixtures with the different types of polyols used for the different applications in order to obtain the desired manufactured article features in terms of density, mechanical and insulation properties, with

the possibility, therefore, of a more generalized use of the foaming agent which changes, depending on the applications, only the composition.

[0043] Azeotropic or near azeotropic compositions are added to the formulations in amounts in the range 1-15% by weight on the total preparation, including the same foaming agent. Preferably 1.5-10% by weight, more preferably 1.5-8% by weight on the total formulation for the foam preparation.

[0044] The mentioned compositions can be advantageously used in combination with H₂O and/or CO₂, for example gas phase.

[0045] In particular they can be used in combination with water, as in the past it was done for the CFC 11, CF 11 "reduce"-based formulations and today it is commonly done for the HCFC 141b-based formulations.

[0046] Water can be added to the formulations in amount in the range 0.5-7, preferably 1-6, and more preferably 1-4 parts by weight on one hundred parts of polyol.

[0047] The CO₂ can be used in concentrations in the range 0.6-10 parts, preferably 1-8 parts by weight on one hundred parts by weight of polyol.

[0048] The mixtures of the invention can be used in combination with stabilizing agents in order to limit the radical decomposition reactions which, as known, are favoured by the temperature, by the presence of metals and by very reactive polyurethane formulations (for example due to polyols and/or catalysts of basic nature used in such formulations).

[0049] The degradation reactions especially concerning the mixtures containing HFC 356 ffa and 365 mfc, can be prevented or reduced by the use of nitroparaffins and/or organic substances having double bond double bonds in the molecule.

[0050] The stabilizing agents are generally used in amounts of 0.1-5% by weight.

[0051] Furthermore the compositions described at points I, II, III, VII, VIII, IX, X, XI, XII, XIII, A, B, C, G, H, I, L, M can be used for the preparation of thermoplastic foams. These compositions can be used as foaming agents above all for foamed polystyrenes and polyethylenes; these materials were prepared in the past by using, as main foaming agents, dichlorodifluoromethane (CFC 12), CFC 11 or mixtures thereof. At present polystyrenes and polyethylenes for thermal insulation applications are produced by using HCFC-based mixtures (HCFC 22: chlorotrifluoro methane; HFC 142b: 1 chloro-1,1 difluoro ethane), which however have been restricted for their environmental impact. The above compositions of the invention used for the preparation of foamed polystyrenes and polyethylenes can be advantageously used in combination with foaming agents selected from CO₂, HFC 134a (1,1,1,2 tetrafluoroethane), HFC 227ea, HFC 152a (1,1 difluoroethane), HFC 236ea (1,1,1,2,3,3 hexafluoropropane) and their binary mixtures. The latter can be used in amount up to 95% by weight of the foaming agent. The amount of the foaming agent to be used for the foamed thermoplastic polymer synthesis is in the range 5-30% by weight on the thermoplastic polymer.

[0052] The following examples are given for illustrative but not limitative purpose of the present invention.

EXAMPLE 1

Azeotropic or near azeotropic behaviour evaluation

[0053] The mixture of known composition and weight is introduced in a small glass cell, previously evacuated, having an internal volume equal to about 20 cm³, equipped with metal connections, feeding valve and a pressure transducer to evaluate the system vapour pressure.

[0054] The filling volumetric ratio is initially equal to about 0.8%v.

[0055] The cell is introduced in a thermostatic bath and the temperature is slowly changed until obtaining a vapour pressure equilibrium value equal to 1.013 bar. The corresponding temperature is recorded and it represents the mixture boiling temperature at the 1.013 bar pressure.

[0056] The temperature is measured close to the equilibrium cell with a thermometer the accuracy of which is equal to ± 0.01 °C; particular attention was paid so that the external temperature measured in the bath is really the internal one of the cell.

[0057] By changing the mixture composition it is possible to estimate possible deviations with respect to the ideality and therefore to identify the azeotropic composition which, as said, will be characterized by an absolute minimum or maximum with respect to the pure components.

[0058] In order to confirm the azeotropic or near azeotropic behaviour, the mixture characterized by a minimum or a maximum in the boiling temperature and others identified close to the azeotrope were subjected to evaporation test at the azeotrope constant temperature.

[0059] The cell content is removed at constant temperature by evaporation until having a loss corresponding to 50% by weight of the initial amount.

[0060] From the evaluation of the initial and final pressure the per cent variation of the vapour pressure is calculated: if the decrease is equal to zero the mixture in those conditions is an azeotrope, if the decrease is < 10% its behaviour

is of a near azotrope.

[0061] It is known that a near azeotropic mixture has a behaviour closer and closer to a true azeotrope if the per cent variation is lower and lower and near zero.

[0062] As a further confirmation of the azeotropic and near azeotropic behaviour, together with the above reported evaluations, analyses of the composition of some mixtures object of the present invention, have been carried out by gaschromatographic method before and after the evaporation test.

[0063] The azeotropic mixtures maintain unchanged, within the limits of the error of the analytical methods, the composition after the liquid evaporation, while in the case of near azeotropic systems, limited composition variations are observed.

[0064] In all the measurements reported in Tables from 2 to 13 the visual observation of the liquid phase at its normal boiling temperature has at any rate shown that no phase separations took place and that the solutions were limpid and homogeneous.

Table 1

Chemical-physical and toxicological characteristics of hydrofluoropolyethers				
Chemical formula	HCF ₂ OCF ₂ OCF ₂ H	HCF ₂ OCF ₂ CF ₂ OCF ₂ H	CCl ₃ F CFC 11	CCl ₂ FCH ₃ HCFC 141b
Molecular mass	184.04	234.05	137.37	116.94
ODP CFC 11=1	0	0	1	0.11
GWP lifetime, years	<10	<10	55	10.8

Table 2

boiling temperature evaluation at the pressure of 1.013 bar HCF ₂ OCF ₂ OCF ₂ H/n-pentane binary mixture	
COMPOSITION HCF ₂ OCF ₂ OCF ₂ H (% by weight)	BOILING TEMPERATURE (°C)
0	35.79
12.6	26.42
25.9	23.00
50.0	21.45
61.9	21.32
74.9	21.35
83.4	21.49
87.0	21.70
95.6	25.18
100	35.39

Table 2a

evaluation of the azeotropic and near azeotropic behaviour by determination of the vapour pressure per cent variation after evaporation of 50% of the initial liquid mass			
Initial composition (% by wt.) HCF ₂ OCF ₂ OCF ₂ H/ n-pentane	Temperature (°C)	Initial pressure (bar)	$\Delta P/P \times 100$ (%)
61.9/38.1	21.32	1.013	0
50.3/49.7	21.32	1.010	2.47
84.3/15.7	21.32	1.006	3.08

Table 3

evaluation of the boiling temperature at the pressure of 1.013 bar HCF ₂ OCF ₂ OCF ₂ H/iso-pentane binary mixture	
COMPOSITION HCF ₂ OCF ₂ OCF ₂ H (% by wt.)	BOILING TEMPERATURE (°C)
0	27.18
14.2	21.02
20.4	20.00
39.5	17.70
61.0	17.40
63.1	17.35
80.1	17.68
90.4	19.80
100	35.39

Table 4a

evaluation of the azeotropic and near azeotropic behaviour by determination of the vapour pressure per cent variation after evaporation of 50% of the initial liquid mass			
Initial composition (% by wt.) HCF ₂ OCF ₂ OCF ₂ H/ iso-pentane	Temperature (°C)	Initial pressure (bar)	$\Delta P/P \times 100$ (%)
63.0/37.0	17.35	1.013	0
39.0/61.0	17.35	1.003	1.49
79.8/20.2	17.35	1.003	4.79

Table 4

evaluation of the boiling temperature at the pressure of 1.013 bar $\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$ /acetone binary mixture	
COMPOSITION $\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$ (% by wt.)	BOILING TEMPERATURE (°C)
0	56.50
28.1	57.88
41.7	58.11
51.0	57.98
61.2	56.63
74.8	53.62
100	35.39

Table 4a

evaluation of the azeotropic and near azeotropic behaviour by determination of the vapour pressure per cent variation after evaporation of 50% of the initial liquid mass.				
Initial composition (% by wt.) $\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$ / acetone	Temperature (°C)	Initial pressure (bar)	New composition after evaporation of 50% by weight of the liquid (% by wt.) $\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$ / acetone	$\Delta/P \times 100$ (%)
41.7/58.3	58.11	1.013	41.8/58.2	0
28.0/72.0	58.11	1.021	31.1/68.9	0.88
50.4/49.6	58.11	1.019	49.7/50.3	1.37

Table 5

evaluation of the boiling temperature at the pressure of 1.013 bar $\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$ /HFC 365 mfc binary mixture	
COMPOSITION $\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$ (% by wt.)	BOILING TEMPERATURE (°C)
0	40.09
10.0	36.89
20.0	34.92
30.0	33.71

EP 0 980 890 A1

Table 5 (continued)

evaluation of the boiling temperature at the pressure of 1.013 bar $\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$ /HFC 365 mfc binary mixture	
COMPOSITION $\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$ (% by wt.)	BOILING TEMPERATURE (°C)
40.1	33.01
50.1	32.66
60.1	32.60
75.0	33.13
80.0	33.54
100	35.39

Table 5a

evaluation of the azeotropic and near azeotropic behaviour by determination of the vapour pressure per cent variation after evaporation of 50% of the initial liquid mass			
Initial composition (% by wt.) $\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$ / HFC 365mfc	Temperature (°C)	Initial pressure (bar)	$\Delta P/P \times 100$ (%)
60.1/39.9	32.60	1.013	0
21.0/78.9	32.60	0.937	5.21
82.1/17.9	32.60	0.968	7.73

Table 6

evaluation of the boiling temperature at the pressure of 1.013 bar $\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$ /HFC 356 ffa binary mixture	
COMPOSITION $\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$ (% by wt.)	BOILING TEMPERATURE (°C)
0	24.71
10.1	24.16
19.9	24.05
29.9	24.22
40.0	24.65
49.9	25.29
60.1	26.24

Table 6 (continued)

evaluation of the boiling temperature at the pressure of 1.013 bar $\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}/\text{HFC 356 ffa}$ binary mixture	
COMPOSITION $\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$ (% by wt.)	BOILING TEMPERATURE (°C)
70.1	27.60
80.1	29.65
100	35.39

Table 6a

evaluation of the azeotropic and near azeotropic behaviour by determination of the vapour pressure per cent variation after evaporation of 50% of the initial liquid mass			
Initial composition (% by wt.) $\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}/\text{HFC 356 ffa}$	Temperature (°C)	Initial pressure (bar)	$\Delta P/P \times 100$ (%)
19.9/80.1	24.05	1.013	0
4.2/95.8	24.05	1.000	0.41
38.2/61.8	24.05	0.994	2.21

Table 7

evaluation of the boiling temperature at the pressure of 1.013 bar $\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}/\text{methoxymethyl methyl ether}$ binary mixture	
COMPOSITION $\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$, % by wt.	BOILING TEMPERATURE, °C
0	41.96
20.1	42.80
27.5	43.05
38.1	43.40
50.6	43.78
59.1	43.74
60.2	43.76
65.0	43.53
72.1	42.95
78.7	41.66

Table 7 (continued)

evaluation of the boiling temperature at the pressure of 1.013 bar $\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$ /methoxymethyl methyl ether binary mixture	
COMPOSITION $\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$, % by wt.	BOILING TEMPERATURE, °C
100	35.39

Table 7a

evaluation of the azeotropic and near azeotropic behaviour by determination of the vapour pressure per cent variation after evaporation of 50% of the initial liquid mass			
Initial composition (% by wt.) $\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$ /methoxymethyl methyl ether	Temperature (°C)	Initial pressure (bar)	$\Delta P/P \times 100$ (%)
59.1/40.9	43.74	1.013	0
72.1/27.9	43.74	1.045	2.39
27.5/72.5	43.74	1.041	2.02

Table 8

evaluation of the boiling temperature at the pressure of 1.013 bar $\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$ /n-hexane binary mixture	
COMPOSITION $\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$ (% by wt.)	BOILING TEMPERATURE (°C)
0	68.00
15.4	43.86
34.0	35.15
50.8	33.12
65.6	32.42
74.7	32.10
78.1	32.15
90.1	32.22
100	35.39

Table 8a

evaluation of the azeotropic and near azeotropic behaviour by determination of the vapour pressure per cent variation after evaporation of 50% of the initial liquid mass

Initial composition (% by wt.) HCF ₂ OCF ₂ OCF ₂ H/ n-hexane	Temperature (°C)	Initial pressure (bar)	ΔP/Px100 (%)
74.7/25.3	32.10	1.013	0
65.6/34.4	32.10	1.006	0.60
90.1/9.9	32.10	1.011	0.89

Table 9

evaluation of the boiling temperature at the pressure of 1.013 bar HCF₂OCF₂CF₂OCF₂H/n-pentane binary mixture

COMPOSITION HCF ₂ OCF ₂ CF ₂ OCF ₂ H (% by wt.)	BOILING TEMPERATURE (°C)
0	35.79
17.3	31.75
29.1	31.52
60.8	31.2
68.0	31.04
72.1	31.08
74.3	31.15
79.3	31.25
84.3	31.77
93.4	35.83
100	58.21

Table 9a

azeotropic and near azeotropic behaviour evaluation by determination of the vapour pressure per cent variation after evaporation of 50% of the initial liquid mass			
Initial composition (% by wt.) HCF ₂ OCF ₂ CF ₂ OCF ₂ H/ n-pentane	Temperature (°C)	Initial pressure (bar)	$\Delta P/P \times 100$ (%)
60.8/39.2	31.02	1.013	0
17.3/82.7	31.02	1.002	4.59
74.3/25.7	31.02	1.008	4.36

Table 10

boiling temperature evaluation at the pressure of 1.013 bar HCF ₂ OCF ₂ CF ₂ OCF ₂ H/acetone binary mixture	
COMPOSITION HCF ₂ OCF ₂ CF ₂ OCF ₂ H (% by wt.)	BOILING TEMPERATURE (°C)
0	56.50
15.5	56.83
30.8	58.23
40.7	59.45
58.6	62.87
70.0	65.04
79.4	65.96
85.5	65.28
89.9	64.41
100	58.21

Table 10a

azeotropic and near azeotropic behaviour evaluation by determination of the vapour pressure per cent variation after evaporation of 50% of the initial liquid mass				
Initial composition (% by wt.) HCF ₂ OCF ₂ CF ₂ OCF ₂ H/ acetone	Temperature (°C)	Initial pressure (bar)	New composition after liquid evaporation of 50% by weight HCF ₂ OCF ₂ CF ₂ OCF ₂ H/acetone (% by wt.)	$\Delta P/P \times 100$ (%)
79.5/20.5	65.96	1.013	79.3/20.7	0

Table 10a (continued)

azeotropic and near azeotropic behaviour evaluation by determination of the vapour pressure per cent variation after evaporation of 50% of the initial liquid mass				
Initial composition (% by wt.) HCF ₂ OCF ₂ CF ₂ OCF ₂ H/ acetone	Temperature (°C)	Initial pressure (bar)	New composition after liquid evaporation of 50% by weight HCF ₂ OCF ₂ CF ₂ OCF ₂ H/acetone (% by wt.)	ΔP/Px100 (%)
69.5/30.5	65.96	1.044	73.9/26.1	2.78
84.8/15.2	65.96	1.035	82.5/17.5	2.90

Table 11

boiling temperature evaluation at the pressure of 1.013 bar HCF ₂ OCF ₂ CF ₂ OCF ₂ H/n-hexane binary mixture	
COMPOSITION HCF ₂ OCF ₂ CF ₂ OCF ₂ H (% by wt.)	BOILING TEMPERATURE (°C)
0	68.00
20.6	56.24
39.7	48.81
59.9	46.74
73.8	46.66
78.7	46.76
89.9	49.00
100	58.21

Table 11a

azeotropic and near azeotropic behaviour evaluation by determination of the vapour pressure per cent variation after evaporation of 50% of the initial liquid mass			
Initial composition (% by wt.) HCF ₂ OCF ₂ CF ₂ OCF ₂ H/ n-hexane	Temperature (°C)	Initial pressure (bar)	ΔP/Px100 (%)
73.8/26.2	46.66	1.013	0
39.8/60.2	46.66	0.938	7.57
89.9/10.1	46.66	0.935	8.02

Table 12

boiling temperature evaluation at the pressure of 1.013 bar $\text{HCF}_2\text{OCF}_2\text{CF}_2\text{OCF}_2\text{H}$ /ethyl alcohol binary mixture	
COMPOSITION $\text{HCF}_2\text{OCF}_2\text{CF}_2\text{OCF}_2\text{H}$ (% by wt.)	BOILING TEMPERA- TURE (°C)
0	78.50
20.6	72.35
48.9	63.70
62.6	60.12
80.0	57.33
89.7	56.07
94.7	55.65
98.0	55.75
99.0	56.02
100	58.21

Table 12a

azeotropic and near azeotropic behaviour evaluation by determination of the vapour pressure per cent variation after evaporation of 50% of the initial liquid mass				
Initial composition (% by wt.) $\text{HCF}_2\text{OCF}_2\text{CF}_2\text{OCF}_2\text{H}$ / ethyl alcohol	Temperature (°C)	Initial pressure (bar)	New composition after evaporation of 50% by weight of the liquid (% by wt.) $\text{HCF}_2\text{OCF}_2\text{CF}_2\text{OCF}_2\text{H}$ / ethyl alcohol	$\Delta P/P \times 100$ (%)
94.7/5.3	55.65	1.013	95.0/5.0	0
79.4/20.6	55.65	0.954	75.6/24.4	1.26
99.0/1.0	55.65	1.005	99.3/0.7	2.99

Table 13

evaluation of the azeotropic behaviour of ternary mixtures by determination of the vapour pressure per cent variation after evaporation of 50% of the initial liquid mass			
Ternary mixtures			
Initial composition (% by wt) $\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}/\text{HCF}_2\text{OCF}_2\text{CF}_2\text{OCF}_2\text{H}/$ acetone	Boiling temperature (°C)	Initial pressure (bar)	$\Delta P/P \times 100$ (%)
12.0/18.0/70.0	57.75	1.013	3.16

Table 13 (continued)

evaluation of the azeotropic behaviour of ternary mixtures by determination of the vapour pressure per cent variation after evaporation of 50% of the initial liquid mass			
Ternary mixtures			
Initial composition (% by wt) HCF ₂ OCF ₂ OCF ₂ H/HCF ₂ OCF ₂ CF ₂ OCF ₂ H/ acetone	Boiling temperature (°C)	Initial pressure (bar)	$\Delta P/P \times 100$ (%)
HCF ₂ OCF ₂ OCF ₂ H/HCF ₂ OCF ₂ CF ₂ OCF ₂ H n- pentane 30.0/20.0/50.0	25.50	1.013	0.30

EXAMPLE 2**15 Use of HFPE-based mixtures as foaming agents for the preparation of rigid polyurethanes**

[0065] Foams have been prepared according to the following procedure:

In a polyethylene cylindrical container (diameter 12 cm; height 18 cm) 100 g of polyol, the required water amount for each kind of formulation and the foaming agent used for the test, are introduced.

20 [0066] The content is mixed with mechanical stirrer for one minute at the rate of 1900 rpm, then isocyanate is added and stirring is continued at the same speed for 15 seconds.

[0067] The foam is allowed to freely expand until the completion of the reaction.

[0068] A foam portion is drawn in the central part of the foam for the visual observation of the homogeneity, of the cellularity properties of the foam and for the density determination.

25 [0069] The data are reported in Table 15 in comparison with those obtained with CFC 11 and HCFC 141b (α and β comparative examples).

Table 14

	Example α (comp)	Example β (comp)	Example γ	Example δ	Example ϵ
Polyol* polyether (g)	100	100	100	100	100
Water pbw (g)	2	2	2.6	2.7	2.6
Aminic catalyst † pbw (g)	2.5	2.5	2.5	2.5	2.5
CFC 11 pbw (g)	30*				
HCFC 141b pbw (g)		28§			
HFPE1/ HFC 365mfc (60/40) pbw (g)			29.8*		
HFPE1/ HFC 356ffa (20)(80) pbw (g)				28.5*	
HFPE1/ HFPE2/ n-pentane (18)(72) (10) pbw (g)					33*
ISOCYA- NATE ‡ pbw (g)	160	160	170	175	170
Density kg/m³	30	29.7	30.0	29.8	30.0
Foam appearance	GOOD	GOOD	GOOD	GOOD	GOOD

HFPE1 = $\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$

HFPE2 = $\text{HCF}_2\text{OCF}_2\text{CF}_2\text{OCF}_2\text{H}$

*: non flammable

§: flammable

‡: polyol polyether with a number of hydroxyl equal to 500
mg KOH/g and containing silicone surfactant

(AF 9930/031.ESF)

♦: N,N-dimethyl cyclohexylamine

♣: Polymeric methylenediphenylisocyanate (MDI)-DESMODUR

44V20 by Bayer

pbw: parts by weight per 100 g of polyol

[0070] The HFPE-based mixtures allow to obtain polyurethane foams with good homogeneity and cellularity characteristics with densities similar to the reference products.

[0071] Sufficiently low densities (about 30Kg/m³) are obtained with amounts of fluorinated foaming agent and water comparable with the amounts used in the reference formulations with CFC 11 and HCFC 141b.

[0072] A further advantage given by the mixtures containing HFPE is that to eliminate or limit the inflammability due to the other flammable components present in the mixture (n-pentane, HFC 365 mfc, HFC 356 ffa) with remarkable advantages in terms of foaming agent handling and in terms of reaction with fire of the final polyurethanic manufactured articles.

Claims

1. Use as foaming agents having a low environmental impact of azeotropic or near azeotropic compositions, based on difluoromethoxy-bis(difluoromethyl ether) and/or 1-difluoromethoxy-1,1,2,2-tetrafluoroethyl difluoromethyl ether, essentially consisting of:

		composition % by weight
I)	difluoromethoxy bis(difluoromethyl ether) (HCF ₂ OCF ₂ OCF ₂ H);	1-95
	n-pentane	99-5
II)	difluoromethoxy bis(difluoromethyl ether) (HCF ₂ OCF ₂ OCF ₂ H);	1-99
	iso-pentane	99-1
III)	difluoromethoxy bis(difluoromethyl ether) (HCF ₂ OCF ₂ OCF ₂ H);	1-60
	dimethyl ketone (acetone)	99-40
IV)	difluoromethoxy bis(difluoromethyl ether) (HCF ₂ OCF ₂ OCF ₂ H);	1-99
	1,1,1,3,3-pentafluorobutane (CF ₃ CH ₂ CF ₂ CH ₃ , HFC 365 mfc)	99-1
V)	difluoromethoxy bis(difluoromethyl ether) (HCF ₂ OCF ₂ OCF ₂ H);	1-40
	1,1,1,4,4,4-hexafluorobutane (CF ₃ CH ₂ CH ₂ CF ₃ , HFC 356 ffa)	99-60
VI)	difluoromethoxy bis(difluoromethyl ether) (HCF ₂ OCF ₂ OCF ₂ H);	1-96
	methoxymethyl methylether	99-14
VII)	difluoromethoxy bis(difluoromethyl ether) (HCF ₂ OCF ₂ OCF ₂ H);	30-99
	n-hexane	70-1
VIII)	1-difluoromethoxy 1,1,2,2-tetrafluoroethyl difluoromethyl ether (HCF ₂ OCF ₂ CF ₂ OCF ₂ H);	1-93
	n-pentane	99-7

(continued)

		composition % by weight
IX)	1-difluoromethoxy 1,1,2,2-tetrafluoroethyl difluoromethyl ether ($\text{HCF}_2\text{OCF}_2\text{CF}_2\text{OCF}_2\text{H}$); dimethyl ketone (acetone)	30-99 70-1
X)	1-difluoromethoxy 1,1,2,2-tetrafluoroethyl difluoromethyl ether ($\text{HCF}_2\text{OCF}_2\text{CF}_2\text{OCF}_2\text{H}$); n-hexane	15-99 85-1
XI)	1-difluoromethoxy 1,1,2,2-tetrafluoroethyl difluoromethyl ether ($\text{HCF}_2\text{OCF}_2\text{CF}_2\text{OCF}_2\text{H}$); ethyl alcohol	5-99 95-1

2. Use of azeotropic or near azeotropic compositions according to claim 1 essentially consisting of:

		composition % by weight
I)	difluoromethoxy bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$); n-pentane	25-95 75-5
II)	difluoromethoxy bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$); iso-pentane	25-98 75-2
III)	difluoromethoxy bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$); dimethyl ketone (acetone)	20-60 80-40
IV)	difluoromethoxy bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$); 1,1,1,3,3-pentafluorobutane ($\text{CF}_3\text{CH}_2\text{CF}_2\text{CH}_3$, HFC 365 mfc)	10-98 90-2
V)	difluoromethoxy bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$); 1,1,1,4,4,4-hexafluorobutane ($\text{CF}_3\text{CH}_2\text{CH}_2\text{CF}_3$, HFC 356 ffa)	10-40 90-60
VI)	difluoromethoxy bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$); methoxymethyl methylether	25-96 75-14
VII)	difluoromethoxy bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$); n-hexane	35-98 65-2
VIII)	1-difluoromethoxy 1,1,2,2-tetrafluoroethyl difluoromethyl ether ($\text{HCF}_2\text{OCF}_2\text{CF}_2\text{OCF}_2\text{H}$); n-pentane	25-93 75-7
IX)	1-difluoromethoxy 1,1,2,2-tetrafluoroethyl difluoromethyl ether ($\text{HCF}_2\text{OCF}_2\text{CF}_2\text{OCF}_2\text{H}$); dimethyl ketone (acetone)	50-98 50-2
X)	1-difluoromethoxy 1,1,2,2-tetrafluoroethyl difluoromethyl ether ($\text{HCF}_2\text{OCF}_2\text{CF}_2\text{OCF}_2\text{H}$); n-hexane	25-98 75-2
XI)	1-difluoromethoxy 1,1,2,2-tetrafluoroethyl difluoromethyl ether ($\text{HCF}_2\text{OCF}_2\text{CF}_2\text{OCF}_2\text{H}$); ethyl alcohol	10-98 90-2

3. Use of azeotropic compositions according to claims 1 and 2 in correspondence of which an absolute minimum or maximum of the boiling temperature at the pressure of 1.013 bar with respect to the pure products is noticed, defined as follows:

5

10	A) difluoromethoxy-bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$); n-pentane	62% by wt. 38% by wt.
	B) difluoromethoxy-bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$); iso-pentane	63% by wt. 36% by wt.
15	C) difluoromethoxy-bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$); dimethyl ketane (acetone)	42% by wt. 58% by wt.
	D) difluoromethoxy-bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$); 1,1,1,3,3-pentafluorobutane ($\text{CF}_3\text{CH}_2\text{CF}_2\text{CH}_3$, HFC 365 mfc)	60% by wt. 40% by wt.
20	E) difluoromethoxy-bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$); 1,1,1,4,4,4-hexafluorobutane ($\text{CF}_3\text{CH}_2\text{CH}_2\text{CF}_3$, HFC 356 ffa)	20% by wt. 80% by wt.
	F) difluoromethoxy-bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$); methoxymethyl methyl ether	59% by wt. 41% by wt.
25	G) difluoromethoxy-bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$); n-hexane	75% by wt. 25% by wt.
30	H) 1-difluoromethoxy-1,1,2,2-tetrafluoroethyl difluoromethyl ether ($\text{HCF}_2\text{OCF}_2\text{CF}_2\text{OCF}_2\text{H}$); n-pentane	61% by wt. 39% by wt.
	I) 1-difluoromethoxy-1,1,2,2-tetrafluoroethyl difluoromethyl ether ($\text{HCF}_2\text{OCF}_2\text{CF}_2\text{OCF}_2\text{H}$); dimethyl ketone (acetone)	79% by wt. 21% by wt.
35	L) 1-difluoromethoxy-1,1,2,2-tetrafluoroethyl difluoromethyl ether ($\text{HCF}_2\text{OCF}_2\text{CF}_2\text{OCF}_2\text{H}$); n-hexane	74% by wt. 26% by wt.
	M) 1-difluoromethoxy-1,1,2,2-tetrafluoroethyl difluoromethyl ether ($\text{HCF}_2\text{OCF}_2\text{CF}_2\text{OCF}_2\text{H}$); ethyl alcohol	95% by wt. 5% by wt.

- 40 4. Use as foaming agents of near azeotropic compositions according to claims 1 and 2 essentially consisting of:

45		composition % by wt.
	II) difluoromethoxy-bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$); iso-pentane	1-99 99-1
50	III) difluoromethoxy-bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$); dimethyl ketone (acetone)	1-60 99-40
	IV) difluoromethoxy-bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$); 1,1,1,3,3-pentafluorobutane ($\text{CF}_3\text{CH}_2\text{CF}_2\text{CH}_3$, HFC 365 mfc)	1-99 99-1
55	V) difluoromethoxy-bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$); 1,1,1,4,4,4-hexafluorobutane ($\text{CF}_3\text{CH}_2\text{CH}_2\text{CF}_3$, HFC 356 ffa)	1-40 99-60

(continued)

		composition % by wt.
5	VI) difluoromethoxy-bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$); methoxymethyl methyl ether	1-96 99-14

wherein the difluoromethoxy-bis(difluoromethyl ether) part contains up to 40% by weight of 1-difluoromethoxy-1,1,2,2-tetrafluoroethyl difluoromethyl ether.

- 10 5. Use as foaming agents of near azeotropic compositions according to claims 1 and 2 essentially consisting of: composition

		% by wt.
15	IX) 1-difluoromethoxy-1,1,2,2-tetrafluoroethyl difluoromethyl ether ($\text{HCF}_2\text{OCF}_2\text{CF}_2\text{OCF}_2\text{H}$); dimethyl ketone (acetone)	30-99 70-1
20	X) 1-difluoromethoxy-1,1,2,2-tetrafluoroethyl difluoromethyl ether ($\text{HCF}_2\text{OCF}_2\text{CF}_2\text{OCF}_2\text{H}$); n-hexane	15-99 85-1

25 wherein 1-difluoromethoxy-1,1,2,2-tetrafluoroethyl difluoromethyl ether contains up to 40% by weight of difluoromethoxy-bis(difluoromethyl ether).

- 30 6. Use as foaming agents of near azeotropic compositions according to claims 1 and 2 essentially consisting of:

		composition % by wt.
35	I) difluoromethoxy-bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$); n-pentane	1-95 99-5
	VII) difluoromethoxy-bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$); n-hexane	30-99 70-1

40 wherein difluoromethoxy-bis(difluoromethyl ether) contains up to 50% of 1-difluoromethoxy-1,1,2,2-tetrafluoroethyl difluoromethyl ether.

- 45 7. Use as foaming agents of near azeotropic compositions according to claims 1 and 2 essentially consisting of:

		composition % by wt.
50	VIII) 1-difluoromethoxy-1,1,2,2-tetrafluoroethyl difluoromethyl ether ($\text{HCF}_2\text{OCF}_2\text{CF}_2\text{OCF}_2\text{H}$); n-pentane	1-93 99-7
55	X) 1-difluoromethoxy-1,1,2,2-tetrafluoroethyl difluoromethyl ether ($\text{HCF}_2\text{OCF}_2\text{CF}_2\text{OCF}_2\text{H}$); n-hexane	15-99 85-1

wherein 1-difluoromethoxy-1,1,2,2-tetrafluoroethyl difluoromethyl ether contains up to 50% by weight of difluoromethoxy-bis(difluoromethyl ether).

8. Use as foaming agents of ternary near azeotropic compositions according to claims 1 and 2 essentially consisting of:

		composition % by wt.
XII)	difluoromethoxy-bis (difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$);	1-64
	1,1,1,3,3-pentafluorobutane ($\text{CF}_3\text{CH}_2\text{CF}_2\text{CH}_3$, HFC 365 mfc)	98-1
	hydrocarbon	1-35
XIII)	difluoromethoxy-bis (difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$);	1-22
	1,1,1,4,4,4-hexafluorobutane ($\text{CF}_3\text{CH}_2\text{CH}_2\text{CF}_3$, HFC 356 ffa)	98-43
	hydrocarbon	1-35

9. Use of the compositions according to claim 8 wherein hydrocarbon is selected between n-pentane and iso-pentane.

10. Use of compositions according to claims 8 and 9 wherein hydrocarbon is present in the range 1-20% by weight.

11. Use of azeotropic or near azeotropic compositions according to claims 1-10 wherein the ether portion HFPE1 and/or HFPE2 can contain at least up to 10% by weight of hydrofluoropolyethers having the same structure but with boiling point in the range 5°-80°C.

12. Use as foaming agents, for the preparation of polyurethanes, of the compositions according to claims 1-7 and 11, mentioned at points I, II, IV, V, VI, VII, VIII, X, A, B, D, E, F, G, H and L.

13. Use of the compositions according to claim 12 in amounts in the range 1-15% by weight on the total preparation, including the same foaming agent; preferably 1.5-10% by weight, more preferably 1.5-8% by weight on the total formulation for the foam preparation.

14. Use of the compositions according to claim 12 in combination with H_2O and/or CO_2 .

15. Use of the compositions according to claim 14 wherein the water amount is in the range 0.5-7, preferably 1-6, and more preferably 1-4 parts by weight on one hundred parts of polyol.

16. Use of the compositions according to claim 14 wherein the CO_2 amount is in the range 0.6-10 parts, preferably 1-8 parts by weight on one hundred parts of polyol.

17. Use of the compositions according to claims from 1 to 16 wherein stabilizers for radicalic decomposition reactions are added, the concentration of which is in the range 0.1-5% by weight with respect to the foaming agent.

18. Use as foaming agents for thermoplastic polymers of the compositions according to claims 1-11, mentioned at points I, II, III, VII, VIII, IX, X, XI, XII, XIII, A, B, C, G, H, I, L and M.

19. Use of the compositions according to claim 18 in combination with foaming agents of physical type selected from CO_2 , HFC 134a, HFC 227ea, HFC152a (1,1 difluoroethane), HFC 236ea (1,1,1,2,3,3 hexafluoropropane) or mixtures thereof.

20. Use of the compositions according to claims 18 and 19 in amounts in the range 5-30% by weight on the thermoplastic polymer.

21. Use of the compositions according to claims from 1 to 11 and from 18 to 20 wherein stabilizers for radicalic decom-

position reactions are added, the concentration of which is in the range 0.1-5% by weight with respect to the foaming agent.

22. Polyurethane compositions comprising the foaming compositions according to claims 12-17.

23. Compositions of thermoplastic polymers according to claims 18-21.

5

10

15

20

25

30

35

40

45

50

55

European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 99 11 4824

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
A	US 5 648 016 A (KLUG DIANA LYNN ET AL) 15 July 1997 (1997-07-15) * column 4, line 7,8 * * column 5, line 62 * * claims * -----	1	C08J9/14 C09K5/04
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
			C08J C09K
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 13 December 1999	Examiner Oudot, R
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

EPO FORM 1503 (03.92) (P04C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 99 11 4824

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

13-12-1999

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5648016 A	15-07-1997	US 5605882 A	25-02-1997
		US 5779931 A	14-07-1998
		AT 177137 T	15-03-1999
		AU 4250093 A	30-12-1993
		BR 9306614 A	08-12-1998
		CN 1082088 A	16-02-1994
		DE 69323743 D	08-04-1999
		DE 69323743 T	09-09-1999
		EP 0642560 A	15-03-1995
		ES 2130267 T	01-07-1999
		JP 7507342 T	10-08-1995
		MX 9303120 A	30-06-1994
		WO 9324586 A	09-12-1997

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82